



## ASC Building Products Color Performance Data

Please note that color specific *CRRC Notification of Product Rating* can be produced upon request

PRODUCT DESCRIPTION	CA TITLE 24 & ENERGY STAR						LEED						
	via CRRC listings (data based on color families)				Energy Star		CA Title 24	via Accredited Independent Testing Laboratory (using ASTM C1549, C1371, & E1980)					
	CRRC Reference Number	Solar Reflectance	Thermal Emittance	SRI	Low Slope	High Slope		Solar Reflectance	Thermal Emittance	SRI	Low Slope	High Slope	
<b>BARE ZINCALUME®</b>													
ZINCALUME® Plus	1014-0002	0.68	0.30	65	✓	✓		0.68	0.30	65		✓	
<b>DURATECH® XL COLORS</b>							REFER TO CALIFORNIA ENERGY COMMISSION (CEC) REQ.						
COOL TAHOE BLUE	0818-0027	0.25	0.83	22		✓			0.33	0.84	33		
COOL OLD TOWN GRAY	0818-0039	0.35	0.83	35		✓			0.40	0.84	43		✓
COOL DENALI GREEN	0818-0028	0.25	0.83	22		✓			0.30	0.83	29		
COOL RUSTIC RED	0818-0031	0.35	0.83	35		✓			0.40	0.84	43		✓
COOL LIGHT STONE	0818-0033	0.55	0.83	63		✓			0.60	0.84	70		✓
COOL DESERT BEIGE	0818-0042	0.45	0.83	49		✓			0.51	0.84	58		✓
COOL CHESTNUT BROWN	0818-0034	0.32	0.83	31		✓			0.35	0.83	36		
COOL WEATHERED COPPER	0818-0035	0.32	0.83	31		✓			0.32	0.83	32		
COOL WINTER WHITE	0818-0044	0.70	0.83	84	✓	✓			0.73	0.83	88	✓	✓
COOL SURF WHITE	0818-0036	0.55	0.83	63		✓			0.63	0.84	74		✓
COOL CYPRESS GREEN	0818-0023	0.25	0.83	22		✓			0.49	0.84	55		✓
COOL CANYON RED	0818-0024	0.35	0.83	35		✓			0.42	0.84	45		✓
COOL TAUPE	0818-0025	0.45	0.83	49		✓			0.48	0.83	53		✓
COOL FOREST GREEN	0818-0029	0.32	0.83	31		✓			0.35	0.85	36		
COOL COPPER PENNY	0818-0032	0.35	0.75	32		✓			0.49	0.84	55		✓
COOL CLASSIC BROWN	0818-0041	0.25	0.83	22		✓			0.29	0.84	29		
COOL EVERGLADE	0818-0043	0.32	0.83	31		✓		0.34	0.85	35			
COOL BLACKBERRY	0818-0050	0.25	0.83	22		✓		0.33	0.85	34			
COOL OLD ZINC GRAY	0818-0051	0.35	0.83	35		✓		0.40	0.84	43		✓	
COOL TUMBLEWEED	0818-0052	0.55	0.83	63		✓		0.62	0.84	73		✓	

All ratings listed above are initial readings. Three year performance data is located on the CRRC website.

<sup>A</sup> - Reflectivity data for Bare Galvalume and Zincalume is actual 3 year weathered solar reflectivity data.

Zincalume® is a registered trademark of BlueScope LTD

Rev.3-1-16